

# MONTOPOL BLANCO SATINADO 69 NA



**FAMILY** TRATAMIENTOS DE LA MADERA / SISTEMAS TINTOMÉTRICOS  
**LINE** ACABADOS POLIU. PIG. (L. Y P.)

## DESCRIPTION AND NATURE

Top coat white two-component polyurethane, good whiteness and coverage, ease of application with excellent leveling.

## USAGES

Indoors

Wood

Product for exclusive use in industries regulated by Directive 2010/75 Chapter V.

## PROPERTIES

- Adherence
- Does not turn yellow
- Optimal applicability
- Strongness
- Elasticity
- Fillness power
- Fast drying
- Odourless when dry

## TECHNICAL CHARACTERISTICS

Referencia Color	MONTOPOL BLANCO SATINADO 69
Mixture relation	VOL: 2(Montopol)+1(Cat NA) ; PESO: 2.5+1
Finish	Satin
Specific weight	1,12± 0,05 kg/l
Viscosity	210 +/- 30 SG
Solids in volume	39± 1
Solids in weight	53± 1
Aproximated performance by coat	10-14 m <sup>2</sup> /L
Dry to touch	(20°C HR: 60%): 15-20min
Dry to repaint	(20°C HR: 60%): 2-24 h
Colours	NCS, Ral chart colors (see the Tinting System database)

## SURFACE PREPARING

### New surfaces

New wood:

- The base must be free from foreign materials and/or waste matter.
- Apply to wood with a moisture content of less than 12%.
- Apply to healthy wood that is dry and free from grease and dust.
- Sand down and remove any remains of glue in joints and defects from mechanical processes.
- If the wood shows signs of aging must be pre-sanded and removing dust by brushing or other mechanical means.

### Restoring and maintenance

-Varnished or painted wood:

- If the wood has been varnished with varnishes or paints that have been diluted with white spirit, turpentine, imitation turpentine or solvents for synthetics and oils, these must be removed using a universal stripper or by employing mechanical

# MONTOPOL BLANCO SATINADO 69 NA

means, until the new wood is reached.

- If in doubt remove the varnish, lacquer or enamel above.
- If it is applied on top of polyurethane varnish (polyurethane solvent is recommended for diluting it), sand to open the pore, remove the resulting dust with a brush and re-varnish.
- In any case, check the adhesion on the previous varnish, and in case of doubt, remove it.
- If silicone-based domestic cleaning products have been used for maintenance, it is advisable to sand the wood until they have been completely removed.

## WAY OF USE

### Application notes

- Stir the products until perfectly blended.
- Mix without modifying under any circumstances the proportions.
- Coat thickeners of greater than 130 g/m<sup>2</sup> wet per coat.
- Always sand before applying the top coat
- Do not apply the product at high temperatures or on surfaces exposed to strong insolation.
- Ensure good ventilation while product is drying.
- Do not apply in relative humidity over 80%.
- Before mixing, make sure that the MONTOPOL NA HARDENER is completely transparent.
- Sanding and delete any traces of glue in assembly and machining faults
- Respect the minimum time between hands to avoid removal.
- Respect the maximum time between hands to avoid adhesion problems.

### Solvent for dilution and cleaning

Solvent PU 1410, Solvent cleaning1406

Way of use	Aproximate dilution
Painting brush	0%
Roller	0%
Air-less gun	0-10%
Air-mix gun	0-10%
Aerographic gun	0-15%

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Painted or varnished wood (closed pore) indoor</b>			
<b>MAX</b>	Decapar+ Gama Fondo Montopol + Cat. MS	Gama Gama Fondo Montopol + Cat. MS	IMontopol Blanco Satinado69 + Cat. NA
<b>STD</b>			
<b>Open pore varnished wood</b>			
<b>MAX</b>	Gama Fondo Montopol + Cat. MS		Montopol Blanco Satinado69 + Cat. NA
<b>STD</b>			
<b>Indoor wood</b>			
<b>MAX</b>	Gama Fondo Montopol + Cat. MS	Gama Fondo Montopol + Cat. MS	Montopol Blanco Satinado69 + Cat. NA
<b>STD</b>			

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Product of exclusive use for premises regulated under RD 117/2003 or 1999/13/CE regulations

501625

Fecha de Alta

28-06-2006

Versión

9 - 20/06/2023

# MONTOPOL BLANCO SATINADO 69 NA



**MONTÓ**  
profesional

## NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

5 Kg, 25 Kg