



FAMILY INSTALACIONES DEPORTIVAS
LINE PISCINAS

DESCRIPTION AND NATURE

Satin paint for swimming pools, 100% chlorinated rubber, highly resistant to chemical agents, alkalinity and moisture.

USAGES

Outdoors/Indoors
Cement
Pools

PROPERTIES

Surface leveling
Waterproof
Water resistant
Alacalynity resistance
Do protect the varnished surfaces from atmospherical factors
The product may become discoloured depending on the type and concentration of the disinfectant used.
Good yield
Drying fast
Excellent adhesion

TECHNICAL CHARACTERISTICS

| | |
|---------------------------------|--|
| Referencia Color | MONTOSPORT PISC.POSEIDON PLUS AL CLOR. |
| Finish | Satin |
| Aproximated performance by coat | 6-8 m ² /L |
| Dry to touch | (20° C HR: 60%): 10-30 min, Filled: 3 days |
| Dry to repaint | (20° C HR: 60%): 24 h |
| Colours | Blue 183 |

SURFACE PREPAIRING

New surfaces

Cement mortar:

- Wait until completely set (minimum 30 days).
- Use an abrasive jet to remove any potential efflorescence from the base and neutralise alkaline surfaces.
- Sand down highly polished surfaces to open up the pores.
- Remove any foreign products and/or residues from the base.
- Use outdoor plaster (Plasmont Exteriores) to fill any defects in the base (in PREPARING BASES family, see lines corresponding to powder plasters and prepared fillers to select an appropriate product).
- Treat mouldy bases with Montolimp.
- Apply a very diluted (approx. 30%) first coat.
- Apply one or two equally diluted coats or
- Apply a single 5-15% diluted second coat.

Restoring and maintenance

1. Completely remove any old paint that is flaking or in poor condition.
2. Dull down glossy surfaces to ensure good adhesion.
3. For painted bases, check the solidity, adhesion and nature of the paint to avoid possible incompatibilities and clear off any dust and dirt before repainting. It is recommended that you do not apply it over water-based swimming pool paint.
4. -Use outdoor plaster (Plasmont Exteriores) to fill any defects in the base (in PREPARING BASES family, see lines

corresponding to powder plaster and prepared fillers to select a suitable solution).

5. Walls with mould should first be treated with Montolimp.

6. Apply a very diluted (approx. 30%) first coat.

7. Apply one or two equally diluted coats or

8. -Apply a single 5-15% diluted second coat.

WAY OF USE

Application Notes

Apply on well-dried bases.

You must check the adhesion of the paint to old paint between coats, as it is common to repaint swimming pools regularly, meaning that the adhesion between coats can be greater than the adhesion of the old paint to the base, causing chipping of layers of paint that are weakly adhered.

If you treat the surface with hydrochloric acid to open the pore, clean with plenty of water and leave to dry.

Dilute the product according to the porosity and state of the base.

This product is resistant to chlorine and chlorine derivatives if concentration is within the limits indicated in RD 742/2013, 27th of September.

For any other treatment (floculants, algacides ...), check with the supplier the possibility to be used in painted pools.

Solvent for dilution and cleaning

Solvent 1403

| Way of use | Aproximate dilution |
|--------------------|---------------------|
| Painting brush | 5-15% |
| Roller | 5-15% |
| Air-less gun | 10-20% |
| Air-mix gun | 10-20% |
| Aerographic gun | 10-20% |
| Low pressure turbo | 5-20% |

SYSTEM

Procedures depending of surface type

| | Primer | Intermedium | Finish |
|-----------------------------------|---|-----------------------|---------------|
| Support with mould | | | |
| MAX | Montolimp y Fijamont muy diluido | Poseidón Plus diluido | Poseidón Plus |
| STD | Montolimp y Fijamont muy diluido | | Poseidón Plus |
| Old paintings in bad state | | | |
| MAX | Eliminar y proceder como en buen estado | | POSEIDON PLUS |
| STD | Eliminar y proceder como en buen estado | | POSEIDON PLUS |
| Old painting in good state | | | |
| MAX | Poseidón Plus diluido | | POSEIDÓN PLUS |
| STD | | | POSEIDÓN PLUS |
| Cement | | | |
| MAX | Fijamont muy diluido | Poseidón Plus diluido | POSEIDON PLUS |
| STD | Poseidón Plus diluido | | POSEIDON PLUS |
| Support weak | | | |
| MAX | Fijamont muy diluido | Poseidón Plus Diluido | Poseidón Plus |
| STD | Fijamont muy diluido | | Poseidón Plus |

MONTOSPORT PISCINAS POSEIDON PLUS AL CL.

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

4 L, 15 L