

Fecha de Alta

04-11-2013

Versión

4 - 11/03/2020


FAMILY ALTA DECORACION / SISTEMAS TINTOMÉTRICOS

LINE SISTEMA MICROCEMENTO

DESCRIPTION AND NATURE

Organic polymer-based resin.
Provides adhesion, hardness and workability to the Microcement System products.

USAGES

Microcement System

PROPERTIES

Strongness
Easy application
- Water-based
- Good colour production performance

TECHNICAL CHARACTERISTICS

Referencia Color	MICROCEMENTO RESINA
Mixture relation	Según producto, ver modo de empleo Microcemento.
Specific weight	1,01± 0,05 kg/l
Viscosity	4 +/- 3 PO
Solids in volume	24± 1
Solids in weight	27± 1
VOC	Cat. i/BA 140/140 (2007/2010):1,18 g/l
Aproximated performance by coat	Depending of product usage

Colours	Colourless
---------	------------

SURFACE PREPAIRING
New surfaces

Refer to the Microcement Finish or Microcement Base Technical Data Sheets

Restoring and maintenance

Refer to the Microcement Finish or Microcement Base Technical Data Sheets

WAY OF USE
Application Notes

Mix ratio depending on the product used:

-Microcement Base: 15kg of Part A (Base): 5L of Part B (Microcement Resin)

-Microcement Finish: 12kg of Part A (fine): 5L of Part B (Microcement Resin)

Solvent for dilution and cleaning

Water

Way of use
Aproximate dilution

Fecha de Alta

04-11-2013

Versión

4 - 11/03/2020

SYSTEM

Procedures depending of surface type

Primer

Intermedium

Finish

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

2.5 Kg, 5 Kg